

NEOTEX® Waterproofing Systems

Estimated Service Life for Liquid Waterproofing Membranes



Estimated service life for liquid waterproofing membranes				
Products	Application System	min. Consumption (kg/m ²)	Estimated Dry Film Thickness (mm)	Minimum service life (years)
Neoproof® Polyurea	2 layers	1,2	0,65	30
Neoproof® Polyurea R	2 layers	1,2	0,70	20
Neoproof® Polyurea H	2 layers	1,2	0,70	15
Neoproof® Polyurea C1	1 layer	0,75	0,42	20
Neoproof® Polyurea R + Neoproof® Polyurea	2 layers	0,6 + 0,6	0,68	25
Neoproof® PU W	2 layers	1,2	0,55	11
	3 layers	1,8	0,83	13
	3 layers with Neotextile	2,5-2,7	1,35-1,50	20
	4 layers with Neotextile	3-3,2	1,55-1,70	22
Neorooft®	2 layers	0,7	0,32	10
	3 layers	1,1	0,50	12
	3 layers with Neotextile	1,5-1,7	0,80-0,95	15
	4 layers with Neotextile	1,8-2	0,95-1,10	17
Revinex® Roof	2 layers	1	0,45	8
	3 layers	1,5	0,68	10
	3 layers with Neotextile	2-2,2	1,05-1,20	12
	4 layers with Neotextile	2,5-2,7	1,25-1,40	15
Silatex® Super	2 layers	1	0,40	7
	3 layers	1,5	0,60	8
	3 layers with Neotextile	2-2,2	0,95-1,05	10
	4 layers with Neotextile	2,5-2,7	1,15-1,25	12

* The stated consumptions refer to applications on cementitious surfaces - The actual life time of the waterproofing system may deviate, as it is directly related to the quality of the substrate, the use of the application area, the slopes, the prevailing atmospheric conditions, the project location, etc.

On behalf of **NEOTEX® S.A.**,

NEOTEX AEEV
V. MOIRA STR., 19600 INDUSTRIAL AREA
MANDRA, GREECE
TEL.: +30 210 5557579 • +30 210 5246826
FAX: +30 210 5558482 • VAT: EL094029945

Lampros Ntoumos
Technical Director